

BRITEX[®] ANTI CORROSIVE COATING

High Build Siloxane Based Direct To Metal Coating

Description

BRITEX[®] ANTI CORROSIVE COATING is a single component, high build, direct to metal primer cum-finish coating suitable for well prepared steel for mild to moderate corrosive atmosphere.

BRITEX[®] ANTI CORROSIVE COATING is a low VOC quick drying material for interior and exterior purpose in moderate corrosive environment. The material has good weather ability and moderate abrasion resistance.

Characteristics

Theoretical Coverage*, m ² / L	5.2 – 8.6	Curing Time, @ 30 °C	
Colors	6 Colours	• Touch Dry, hrs	1
Volume Solid, %	67±2	• Handle, hrs	3 - 4
DFT, Microns	75 - 125	• Hard, days	10 -12
Temperature Resistance, °C		Flash Point, °C	29 ± 1
• Continuous	90	Density, gm / cc	1.35 ± 0.05
• Intermittent	120	VOC, grm / L	220 - 250
Application temperature, °C	< 10 to > 45	Over Coating Interval, hrs	10 - 36

* Depending Upon Surface Condition.

Application

- Mild steel coating application.
- Automobile workshops and showrooms.
- Steel roof structures, concrete and cement surfaces.
- Pipe line coatings.
- OEM application.
- Any MS structures.

Advantage

- Good semi glossy to glossy finish.
- Easy to apply, flowable consistency.
- Excellent bond to metal surface.
- Moderate to good chemical resistance.
- Good weather ability.

Application Methodology

□ Surface Preparation

- Remove oil / grease by washing with liquid detergent, followed by acid wash or by burning.
- Remove dust, flakes, or other foreign particles by jet or dry air and prepare the surface for application.
- Preferably achieve a surface profile as per SSPC SP 10 (SA 2½).

□ Material Preparation

- Stir thoroughly **BRITEX[®] ANTI CORROSIVE COATING** with a slow speed drill mixer with a spiral type blade at the bottom of stirrer rod till homogeneous mix is obtained.
- After stirring, wait for the product to settle in order to let entrapped air escape.

□ Application of Material

- Apply **BRITEX® ANTI CORROSIVE COATING** on the prepared surface by brush / roller / airless spray gun with standard equipment having pump ratio minimum 30 : 1.
- Apply **BRITEX® ANTI CORROSIVE COATING** preferably without thinning, if required, add up to 5% BRITEX Thinner for spray application.

Limitations

- Do not apply **BRITEX® ANTI CORROSIVE COATING**
- On surfaces known to, or likely to, suffer from rising dampness, potential osmosis problems or having relative humidity greater than 75 %.
- On to asphalt, weak or infirm concrete, unmodified sand / cement screeds, PVC tiles or sheets, or substrates known to move substantially e.g. steel walkways.

Cleaning & Maintenance

- Clean all tools immediately after use with Xylene. Do not allow material to harden.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately.
- Do not induce vomiting.

Packing

Available in 1 L & 4 L pack.

Storage

Store in a cool dry place, under shed, away from heat.

Shelf Life

36 months in original unopened sealed conditions.

CEYMCO



CEYMCO GLOBAL PRIVATE LIMITED

H.O: 98, MAIN ROAD, PRITHIVIPAKKAM, AMBATTUR, CHENNAI, TAMILNADU - 600053
Factory: 142 - C, SALEM ROAD, NAMAKKAL, TAMILNADU - 637001